



DESCRIPTION

NYCOLUBE 127 CLP is a highly penetrating, mobile liquid operating at temperatures ranging from -54°C to +150°C, based on synthetic oil and containing anti-corrosion and anti-wear additives. It has excellent water-displacing properties as well as high flash point and very low odor.



APPLICATIONS

Cleaning, lubrication and preservation of both small and large calibre weapons generally fitted on ground vehicles or fighter aircrafts.

SPECIFICATIONS * / OEM's & Airframers reference

- Meets MIL-PRF-63460 F Type A
- Approved BT-PS-661A (Belgium)
- Equivalent to DCSEA 501/A

* **Approved:** The product has been approved by the relevant authority. The product is referenced on the applicable qualified product list.

Meets: The product complies with all the requirements of the specification and has not been formally approved or approval is in-progress or the specification is obsolete.

Equivalent: The product complies with the major requirements of the specification.

CHARACTERISTIC	UNIT	TYPICAL RESULT	LIMIT	TEST METHOD
Appearance	-	Brown clear and homogeneous oil	Limpid, Homogeneous	Visual Examination
Density at 20°C	kg/dm ³	0.840	Report	ASTM D4052
Kinematic Viscosity at at 100°C	mm ² /s	3.86	-	ASTM D445
at 40°C		16.3	min. 14.0	
at - 40°C, after evaporation		2502	max. 5000	
Flash Point, COC	°C	188	min. 80	ASTM D92
Pour Point	°C	-75	max. -59	ASTM D97
Steel on steel wear	mm	0.66	max. 0.80	ASTM D4172
Load Wear Index	daN	42	-	ASTM D2783
Weld Load	kg	305	-	
Salt Spray Resistance, 100 h at 35°C	-	Pass	max. 3 pts < 1mm	ASTM B117
Corrosion Test 168 h at 55°C, metal weight loss	mg/cm ²			MIL-PRF-63460 F
Zinc		0.0	max. +/- 1.5	
Aluminium		0.0	max. +/- 0.2	
Brass		0.0	max. +/- 1.0	
Steel		0.0	max. +/- 0.2	
Copper		0.0	max. +/- 1.5	
Magnesium		0.0	max. +/- 0.5	
Cadmium	0.0	max. +/- 1.5		

The values above are typical values. They do not constitute any contractual commitment.

Sales specifications are available on request. The present technical data sheet replaces all the previous editions.