

Page 1 of 5

Product description: AVIONIC CORROSION PREVENTIVE (MIL-PRF-81309H TYPE II & III CLASS 1)

FEATURES:

A medium to heavy duty water displacing, thin film, corrosion preventive compound

KEY BENEFITS:

- Protects electrical connectors from corroding
- Prevents disruption contact between connectors
- Prevents corrosion in the harshest environments
- The cured film of ZC-026 can withstand temperatures as low as -55°C (-67°F) and as high as 85°C (185°F) continuously

Key Benefits Continued On The Next Page



- Protects cables and surfaces as well as other interior and exterior aircraft surfaces
- Can be used for initial protection during shipment and storage and for in-service treatment of critical areas
- Provides superior protection to avionic connectors and components and has lubricating properties to prevent fretting corrosion

Rev: 20082H 07-08-2024







Page 2 of 5

Product description:

AVIONIC CORROSION PREVENTIVE (MIL-PRF-81309H TYPE II & III CLASS 1)

KEY BENEFITS CONTINUED FROM PAGE 1:

- ► The coating can withstand temperatures up to 105°C (221°F) for only 500 hours cumulative
- Free of chromates
- Does not harm most paints, plastic, or insulation
- Penetrates mated connectors to provide corrosion protection for assembly as well as in-service components
- ► Free from heavy metals
- Low toxicity

SPECS:

- Boeing Service Bulletin 737-24A 1148 (QPL), AD 2002-16-03 (QPL)
- Boeing DPM-5707-1 (QPL)

- Embraer E6125209 (QPL)
- MIL-PRF-81309H Type II & III, Class 1 (QPL)
- Sikorsky SS 8536 Type 1 (QPL)

APPLICATIONS:

- ✓ Use on highly critical metal surfaces and avionic components
- ✓ Aerosol application available as D-5026NS
- √ Store at 40°F-100°F (4°C-38°C)
- ✓ For removal of **ZC-026**, use **ZC-640 (D-5640NS)**, **Sur-Prep® 3160**, or **Sur-Prep® 3167**.





Page 3 of 5

Product description:

AVIONIC CORROSION PREVENTIVE (MIL-PRF-81309H TYPE II & III CLASS 1)

PHYSICAL PROPERTIES:

- **Evaporation Rate:** Slower than ether
- ► Fungal Growth per Fed-STD-810 Method 508.7: 0 (No Microbial Growth)
- Outgassing per ASTM E-595
 - Total Mass Loss (TML): 49%
 - Collected Volatile Condensable Material (CVCM): 27.3%
- ► Shelf Life: 3 years from date of shipment
- ► Specific Gravity (H₂O=1): 0.86
- ► Vapor Density: Heavier than air

AVAILABLE PACK SIZES:

D-5026NS

Case of 12 of 16 fl oz (473 mL) Aerosols-007669

Available Pack Sizes Continued On Next Page





Page 4 of 5

Product description:

AVIONIC CORROSION PREVENTIVE (MIL-PRF-81309H TYPE II & III CLASS 1)

AVAILABLE PACK SIZES (CONTINUED FROM PAGE 3):

ZC-026

- Case of 4 each Gallon (4 each of 3.8 Liter) Cans-009415
- 5 Gallon (18.9 Liter) Pails-002095
- 55 Gallon (208 Liter) Drums-002096
- Special Packaging Upon Request

D-5640NS

16 fl oz (473 mL) Aerosol (002070)

ZC-640

- Case of 4 each Gallon (4 each of 3.8 Liter) Cans (009430)
- 5 Gallons (18.9 Liter) (002155)
- > 55 Gallons (208 Liter) (008181)
- Special packaging upon request

Available Pack Sizes Continued On The Next Page







Page 5 of 5

Product description:

AVIONIC CORROSION PREVENTIVE (MIL-PRF-81309H TYPE II & III CLASS 1)

AVAILABLE PACK SIZES (CONTINUED FROM PAGE 4):

Sur-Prep® 3160

- Case of 12 of 16 fl oz (473 mL) Aerosols (010938)
- Case of 4 each Gallon (4 each of 3.8 Liter) Cans (008578)
- ▶ 5 Gallon (18.9 Liter) Pail (008579)
- 55 Gallon (208 Liter) Drum (008580)
- Case of 6 Canisters of Towelettes (100026)
- Case of 100 Individual Towelettes (011844)
- Special packaging upon request

Sur-Prep® 3167

- Case of 12 of 16 fl oz (473 mL) Aerosols (103765)
- Case of 4 each Gallon (4 each of 3.8 Liter) Cans (103762)
- 5 Gallon (18.9 Liter) Pail (103763)
- 55 Gallon (208 Liter) Drum (103764)
- Special packaging upon request

